

SECTION 92

ASPHALTS

Asphalts shall conform to Section 92 of the Caltrans Standard Specifications and these City Standard Specifications.

92-1.02 Grades. - At no time shall the temperature of asphalt in storage be higher than 10°F below the actual flash point of the asphalt.

92-1.03 Test Report. - At the time of delivery of each shipment of paving asphalt by tank car or truck load or fraction thereof, the vendor shall furnish the purchaser with certificate of compliance. The certificate of compliance shall indicate the name of the vendor, type and grade of asphalt delivered, date and point of delivery, contract number or purchase order number, quantity, and the results of specified tests. The certificate of compliance, signed by an authorized representative of the vendor, shall certify that the product delivered conforms to these specifications for the type and grade indicated. The purchaser shall provide the City the certified test reports, when requested by the Engineer, in accordance with the provisions of Section 6-1.07 "Certificates of Compliance."

92-1.04 Applying Asphalt. - Unless otherwise specified, paving asphalts shall be applied at temperatures within the limits given in the following table.

Grade of Asphalt	Pugmill Mixing Temperature °F		Distributor Application Temperature °F	
	Min.	Max.	Min.	Max.
AR-1000	225	275	270	350
AR-2000	275	325	285	350
AR-4000	275	325	290	350
AR-8000	275	325	295	350
AR-16000	300	350	300	350